



Patent
Case No.: 56312US009

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

First Named Inventor: DAMS, RUDOLF J.

Application No.: 10/053001

Group Art Unit: 1754

Filed: January 17, 2002

Examiner: Unknown

Title: WATER SOLUBLE OR WATER DISPERSIBLE
FLUORO-CHEMICAL SILANES FOR RENDERING SUBSTRATES
OIL AND WATER REPELLENT

RECEIVED
DEC 12 2002
10:17:00 MAIL ROOM

CLAIM OF PRIORITY

Commissioner for Patents
Washington, DC 20231

CERTIFICATE OF MAILING

I hereby certify that this correspondence is being deposited with the United States Postal Service as First Class Mail in an envelope addressed to: Commissioner for Patents, Washington, DC 20231 on:

12/6/02
Date

Joyce M. Courtney
Signed by: Joyce M. Courtney

Dear Sir:

Applicant hereby claims priority pursuant to Title 35, United States Code, Section 119, based upon the earlier filed foreign application No. EP 01200208.5, filed on January 19, 2001 in the European Patent Office.

A certified copy of the above-identified earlier-filed foreign application is enclosed. A certified, English language translation of the earlier-filed foreign application is also enclosed.

Respectfully submitted,

December 5, 2002
Date

By: Robert H. Jordan
Robert H. Jordan, Reg. No.: 31,973
Telephone No.: 651-733-6866

Office of Intellectual Property Counsel
3M Innovative Properties Company
P.O. Box 33427
St. Paul, MN 55133-3427
Facsimile No.: 651-736-3833

RECEIVED
DEC 18 2002
TECH CENTER 1600/2900

THIS PAGE BLANK (USPTO)



**Europäisches
Patentamt**

**European
Patent Office**

**Office européen
des brevets**

Bescheinigung

Certificate

Attestation

Die angehefteten Unterlagen stimmen mit der ursprünglich eingereichten Fassung der auf dem nächsten Blatt bezeichneten europäischen Patentanmeldung überein.

The attached documents are exact copies of the European patent application described on the following page, as originally filed.

Les documents fixés à cette attestation sont conformes à la version initialement déposée de la demande de brevet européen spécifiée à la page suivante.

Patentanmeldung Nr. Patent application No. Demande de brevet n°

01200208.5

Der Präsident des Europäischen Patentamts;
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets
p.o.

R C van Dijk

DEN HAAG, DEN
THE HAGUE, 08/01/02
LA HAYE, LE

THIS PAGE BLANK (USPTO)



Europäisches
Patentamt

European
Patent Office

Office européen
des brevets

Blatt 2 der Bescheinigung
Sheet 2 of the certificate
Page 2 de l'attestation

Anmeldung Nr.:
Application no.:
Demande n°: 01200208.5

Anmeldetag:
Date of filing: 19/01/01
Date de dépôt:

Anmelder:
Applicant(s):
Demandeur(s):
3M Innovative Properties Company
St. Paul, Minnesota 55133-3427
UNITED STATES OF AMERICA

Bezeichnung der Erfindung:
Title of the invention:
Titre de l'invention:

Water soluble or water dispersible fluorochemical silanes for rendering substrates oil and water repellent.

In Anspruch genommene Priorität(en) / Priority(ies) claimed / Priorité(s) revendiquée(s)

Staat:
State:
Pays:

Tag:
Date:
Date:

Aktenzeichen:
File no.
Numéro de dépôt:

Internationale Patentklassifikation:
International Patent classification:
Classification internationale des brevets:

C08F20/22, C08F220/22, C08F220/24, C08F20/24, C08F20/38, C08F220/38

Am Anmeldetag benannte Vertragsstaaten:
Contracting states designated at date of filing: AT/BE/CH/CY/DE/DK/ES/FI/FR/GB/GR/IE/IT/LI/LU/MC/NL/PT/SE/TR
Etats contractants désignés lors du dépôt:

Bemerkungen:
Remarks:
Remarques:

THIS PAGE BLANK (USPTO)

25 01. 2001

DESCRIPTION

(63)

**WATER SOLUBLE OR WATER DISPERSIBLE FLUOROCHEMICAL SILANES
FOR RENDERING SUBSTRATES OIL AND WATER REPELLENT**

5

1. Field of the invention

The present invention relates to fluorochemical silanes, in particular oligomeric fluorochemical silanes that can be dissolved or dispersed in water, and to a method of making same. The invention further relates to aqueous compositions of the fluorochemical silane and to a method of treatment of a substrate therewith.

2. Background of the invention.

Fluorochemical compounds are well known and commercially used to render various substrates oil- and water repellent and to provide other desirable properties thereto such as soil repellency and soil release. For example, US 5,292,796 and US 5,453,540 disclose certain fluorochemical oligomers for the treatment of substrates such as, for example, fibrous substrates. The oligomers disclosed are typically functionalised with an isocyanate group to cause reaction with the fibrous substrate surface.

20

Fluorochemical compounds including silanes are also known and commercially available. For example, FC 405 is a fluorochemical silane that is commercially available from 3M Company for rendering substrates such as glass or ceramics oil and water repellent. However, this product is solvent based and it would be desirable to have water based product for treating such substrates as glass or ceramics.

25

US 5,980,992 discloses fluorochemical silanes for the treatment of silicon-containing organic polymeric surfaces to restore the repellency thereof. The silicon-containing organic polymeric surfaces that become spent during their use can be coatings that are based on a fluorochemical oligomer that comprises silane groups. These compositions are however applied from solvent.

30


Fluorochemical compounds that can be applied from water are also known in the art. For example, US 5,274,159 discloses a fluorochemical silane having hydrolysable polyoxyalkylene groups bonded to the silicone atom of the silyl groups. These groups are taught to hydrolyse in the presence of an acid or base catalyst after application to a substrate. However, the obtained oil- and water-repellency properties of the coated substrate and abrasion resistance leave room for further improvement.

Still further aqueous based fluorochemical compositions are disclosed in US 5,550,184 and WO 99/29636. US 5,550,184 discloses a hydrolysed silane emulsion obtained by emulsifying a hydrolysable perfluoroalkoxysilane in water in the presence of an emulsifier. WO 99/29636 discloses aqueous emulsions containing 1) a fluorocarbon silane hydrolysate generated in the presence of a surfactant and 2) a silicate, which provides a clear and smooth coated surface having water repellency and heat resistance when applied to a substrate.

Despite the many known fluorochemical compositions for the treatment of surfaces, there continues to be a desire to find further beneficial fluorochemical compositions and in particular fluorochemical compositions for the treatment of hard surfaces that can be applied in an environmental friendly way from an aqueous based composition. Preferably, such fluorochemical composition will have a high water repellency, high oil repellency and preferably have a high durability. Further desired properties are good stain resistance and/or stain release. Desirably, the compositions are easy to manufacture in a cost effective and convenient way.

3. Summary to the invention.

The present invention provides a water soluble or water dispersible fluorochemical silane represented by the general formula:




(I)

wherein X represents the residue of an initiator or hydrogen;

M^f represents units derived from one or more fluorinated monomer;

M^h represents units derived from one or more non-fluorinated monomer;

M^a represents units having a silyl group represented by the formula:



(II)

5 wherein each of Y^4 , Y^5 and Y^6 independently represents an alkyl group, an aryl group or a hydrolyzable group;

G is a monovalent organic group comprising the residue of a chain transfer agent;


n represents a value of 1 to 100;

m represents a value of 0 to 100;

10 and r represents a value of 0 to 100;

and $n+m+r$ is at least 2;

with the proviso that at least one of the following conditions is fulfilled: (a) G contains a silyl group of the formula:



(III)

15 wherein Y^1 , Y^2 and Y^3 each independently represents an alkyl group, an aryl group or a hydrolyzable group and at least one of Y^1 , Y^2 and Y^3 represents a hydrolyzable water solubilising group or

(b) r is at least 1 and at least one of Y^4 , Y^5 and Y^6 represents a hydrolyzable water solubilizing group.

20

The fluorochemical silane of the invention can be dissolved or dispersed in water and accordingly, aqueous compositions can be prepared therefrom allowing environmental friendly application of the fluorochemical silane. Additionally, the fluorochemical silane of the invention can achieve good oil- and water repellency

25 properties when applied to a substrate and in particular when applied to hard

surfaces. Good stain resistance and stain release may also be obtained. Finally, the fluorochemical silane when applied to a substrate can achieve durable oil- and water repellency properties.

- 5 The present invention further provides aqueous compositions including the fluorochemical silane, a method for making the above fluorochemical silane, and the method of treatment of a substrate with the fluorochemical silane. By the term "aqueous composition" in connection with the present invention is generally meant that a major amount of the composition consists of water, i.e. the composition
- 10 contains at least 51 % by weight of water, preferably at least 80 % by weight of water.

4. Detailed description of the invention.

- The water soluble or water dispersible fluorochemical silanes of this invention,
- 15 corresponding to the general formula I, are generally oligomers that can be prepared by free-radical oligomerization of a fluorochemical monomer and optionally a non-fluorinated monomer in the presence of a chain transfer agent. The oligomers should also include one or more silyl groups that have one or more hydrolyzable water solubilising groups. By the term "water solubilising groups" is meant that
- 20 these groups help solubilising or dispersing the fluorochemical silane in water. These water solubilising groups should also be hydrolyzable under appropriate conditions so that, upon application of the fluorochemical silane to a substrate, these water solubilising groups can be removed from the coating so that such coating can display the desired oil and water repellent properties. The silyl groups having one
- 25 or more hydrolysable water solubilising groups can be included in the fluorochemical silane by copolymerising the fluorochemical monomer with a silyl group-containing monomer or through the use of chain transfer agent that includes a silyl group. Alternatively, a functionalised chain transfer agent or functionalised comonomer can be used which can be reacted with a silyl group containing reagent
- 30 subsequent to the oligomerization. When a silyl group containing monomer or chain transfer agent is used during the free radical oligomerization, such silyl group need not contain the water solubilising groups. Upon oligomerization, the oligomer

may be further reacted with a reactant including a water solubilising group to introduce such groups on the silyl moieties contained in the oligomer.

The total number of units in the oligomer is represented by the sum of n, m and r and is generally at least 2 and preferably at least 3 so as to render the compound oligomeric. The value of n in the fluorochemical oligomer is between 1 and 100 and preferably between 2 and 20. The values of m and r are between 0 and 100 and preferably between 1 and 30. According to a preferred embodiment, the value of m is less than that of n and $n+m+r$ is at least 2. The molecular weight of the fluorochemical oligomers is typically between about 400 and 100000, preferably between 800 and 20000.

The fluorochemical silane of the present invention comprises at least one hydrolyzable water solubilizing group, in order to render the oligomer water soluble or water dispersible. By the term "water soluble" is meant that a concentration of at least 0.1 % by weight, preferably 0.5 % by weight, of the fluorochemical silane can be dissolved in water at ambient temperature. By the term "water dispersible" is meant that a dispersion of at least 0.1 % by weight of the fluorochemical silane in water can be made that is stable for at least 1 hour, preferably for at least 4 hours, without additional emulsifier present. The fluorochemical silane of the present invention preferably contains at least 20 % (based on total weight of the silane), more preferably at least 30 % by weight, most preferably at least 40 % by weight of hydrolysable water solubilizing groups.

The hydrolyzable water solubilizing groups of the fluorochemical silane can be ionic or non-ionic. Typical examples of a hydrolyzable water solubilizing group that are non-ionic include poly(oxyalkylene) groups. An oxyalkylene unit in the poly(oxyalkylene) group preferably has 2 or 3 carbon atoms, such as $-\text{OCH}_2\text{-CH}_2-$, $-\text{OCH}_2\text{-CH}_2\text{-CH}_2-$, and $-\text{OCH}(\text{CH}_3)\text{CH}_2-$, the oxyalkylene units in the poly(oxyalkylene) group can be the same, as in poly(oxyethylene), or present as a mixture, as in straight or branched chain or randomly distributed oxyethylene and oxypropylene units or as in a straight or branched chain of blocks of oxyethylene

units and blocks of oxypropylene units, as long as the poly(oxyalkylene)group remains water soluble or water dispersible. Particularly preferred poly(oxyalkylene) groups are polyoxyethylene and alkoxypolyoxyethylenes that have a molecular weight up to about 1500. Preferably, the number of oxyalkylene units in a

5 poly(oxyalkylene) is between 2 and 120 and more preferably between 2 and 48.


Ionic hydrolysable water solubilizing groups include anionic, cationic and zwitterionic groups. Specific examples of ionic hydrolysable water solubilizing groups include $-\text{OCH}_2\text{CH}_2\text{N}^+(\text{CH}_3)_3\text{I}^-$, $-\text{OCH}_2\text{CH}_2\text{N}^+(\text{CH}_3)_2\text{CH}_2\text{CH}_2\text{CH}_2\text{SO}_3^-$ and $-\text{OCH}_2\text{CH}_2\text{N}^+(\text{CH}_3)_3\text{Cl}^-$.

10

It will further be appreciated by one skilled in the art that the preparation of water soluble or water dispersible fluorochemical silanes according to the present invention results in a mixture of compounds and accordingly, the general formula (I) should be understood as representing a mixture of compounds whereby the indices

15 n, m and r in formula I represent the molar amount of the corresponding unit in the mixture. Accordingly, it will be clear that n, m and r can be fractional values.

The units M^f of the fluorochemical silane are generally derived from fluorochemical monomers corresponding to the formula :



wherein R_f represents a fluoroaliphatic group containing at least 3 carbon atoms or a fluorinated polyether group. Q represents an organic divalent linking group and E^1 represents a free radical polymerizable group.

25 The fluoroaliphatic group R_f in the fluorochemical monomer, is a fluorinated, stable, inert, preferably saturated, non-polar, monovalent aliphatic radical. It can be straight chain, branched chain, or cyclic or combinations thereof. It can contain heteroatoms such as oxygen, divalent or hexavalent sulfur, or nitrogen. R_f is preferably a fully-fluorinated radical, but hydrogen or chlorine atoms can be present

30 as substituents if not more than one atom of either is present for every two carbon atoms. The R_f radical has at least 3 and up to 18 carbon atoms, preferably 3 to 14,


especially 4 to 10 carbon atoms, and preferably contains about 40% to about 80% fluorine by weight, more preferably about 50% to about 78% fluorine by weight. The terminal portion of the R_f radical is a perfluorinated moiety, which will preferably contain at least 7 fluorine atoms, e.g., $CF_3CF_2CF_2-$, $(CF_3)_2CF-$, F_5SCF_2- .

- 5 The preferred R_f radicals are fully or substantially fluorinated and are preferably those perfluorinated aliphatic radicals of the formula $C_nF_{2n+1}-$ where n is 3 to 18, particularly 4 to 10.

The R_f group can also be a perfluoropolyether group. The perfluoropolyether group

- 10 R_f can include linear, branched, and/or cyclic structures, that may be saturated or unsaturated, and substituted with one or more oxygen atoms. It is preferably a perfluorinated group (i.e., all C-H bonds are replaced by C-F bonds). More preferably, it includes perfluorinated repeating units selected from the group of - $(C_nF_{2n})-$, - $(C_nF_{2n}O)-$, - $(CF(Z))-$, - $(CF(Z)O)-$, - $(CF(Z)C_nF_{2n}O)-$, - $(C_nF_{2n}CF(Z)O)-$, - $(CF_2CF(Z)O)-$, and combinations thereof. In these repeating units Z is a
- 15 perfluoroalkyl group, an oxygen-substituted perfluoroalkyl group, a perfluoroalkoxy group, or an oxygen-substituted perfluoroalkoxy group, all of which can be linear, branched, or cyclic, and preferably have about 1 to about 9 carbon atoms and 0 to about 4 oxygen atoms. The terminal groups can be $(C_nF_{2n+1})-$, $(C_nF_{2n+1}O)-$ or
- 20 $(X'C_nF_{2n}O)-$, wherein X' is H, Cl, or Br, for example. Preferably, these terminal groups are perfluorinated. In these repeating units or terminal groups, n is 1 or more, and preferably about 1 to about 4. Particularly preferred approximate average structures for a perfluoropolyether group include $C_3F_7O(CF(CF_3)CF_2O)_pCF(CF_3)-$ and $CF_3O(C_2F_4O)_pCF_2-$ wherein an average value for p is 1 to about 50. As
- 25 synthesized, these compounds typically include a mixture of polymers. The approximate average structure is the approximate average of the mixture of polymers.

- 30 Difunctional fluorochemical monomers can also be used provided the resulting fluorochemical silane remains water soluble or dispersible at least at 0.1% by weight. Accordingly, M^f in formula I can further be derived from a difunctional fluorochemical monomer corresponding to the formula :



wherein Q^a and Q^b each independently represents an organic divalent linking group and E^a and E^b each independently represent a free radical polymerizable group. R^1_f

represents a divalent perfluoropolyether group such as $-(CF(CF_3)CF_2O)_p-$, -

5 $(CF_2O)_p(CF_2CF_2O)_q-$, $-CF(CF_3)(CF_2CF(CF_3)O)_pCF(CF_3)O-$, -

$(CF_2O)_p(CF_2CF_2O)_qCF_2-$, $-(CF_2CF_2O)_p-$, $-(CF_2CF_2CF_2O)_p-$, wherein an average

value for p and q is 1 to about 50. The molecular weight of the difunctional fluorochemical monomer should generally be between about 200 and 1000, more preferably between 300 and 600.


10

The linking groups Q , Q^a and Q^b in the above formulas (IV) and (V) link the fluoroaliphatic or the fluorinated polyether group R_f or R^1_f to the free radical polymerizable group E^1 , E^a or E^b and are generally non-fluorinated organic linking groups. The linking groups preferably contain from 1 to about 20 carbon atoms and

15 may optionally contain oxygen, nitrogen, or sulfur-containing groups or a combination thereof. The linking groups are preferably free of functional groups that substantially interfere with free-radical oligomerization (e.g., polymerizable

olefinic double bonds, thiols, and other such functionality known to those skilled in the art). Examples of suitable linking groups Q include straight chain, branched

20 chain or cyclic alkylene, arylene, aralkylene, oxy, oxo, hydroxy, thio, sulfonyl, sulfoxy, amino, imino, sulfonamido, carboxamido, carbonyloxy, urethanylene, ureylene, and combinations thereof such as sulfonamidoalkylene. Preferred linking groups are selected from the group consisting of alkylene and an organic divalent linking group according to the following formulae :



25

wherein R^1 represents a hydrogen or a linear or branched alkylene having 2 to 4 carbon atoms and R^2 represents a hydrogen or an alkyl having 1 to 4 carbon atoms.

E^1 , E^a and E^b are a free radically polymerizable groups that typically contain an ethylenically unsaturated group capable of undergoing a free radical polymerization.

Suitable groups include, for example, moieties derived from vinyl ethers, vinyl esters, allyl esters, vinyl ketones, styrene, vinyl amide, acrylamides, maleates, fumarates, acrylates and methacrylates. Of these, the esters of alpha, beta unsaturated acids, such as the acrylates and methacrylates are preferred.

5

Fluorochemical monomers $R-Q-E^1$ as described above and methods for the preparation thereof are known and disclosed, e.g., in U.S. Pat. No. 2,803,615. Examples of such compounds include general classes of fluorochemical acrylates, methacrylates, vinyl ethers, and allyl compounds containing fluorinated sulfonamido groups, acrylates or methacrylates derived from fluorochemical telomer alcohols, acrylates or methacrylates derived from fluorochemical carboxylic acids, and perfluoroalkyl acrylates or methacrylates as disclosed in EP-A-526 976.

10




Fluorinated polyetheracrylates or methacrylates are described in U.S. Pat. No. 4,085,137.




15

Preferred examples of fluorochemical monomers include :









20





5



15

wherein R represents methyl, ethyl or n-butyl and u and v are about 1 to 50.

The units M^b of the fluorochemical silane (when present) are generally derived from a non-fluorinated monomer, preferably a monomer consisting of a polymerizable group and a hydrocarbon moiety. Hydrocarbon group containing monomers are well known and generally commercially available. Examples of non-fluorinated

5 monomers from which units M^b can be derived include general classes of ethylenic compounds capable of free-radical polymerization, such as, for example, allyl esters such as allyl acetate and allyl heptanoate; alkyl vinyl ethers or alkyl allyl ethers such as cetyl vinyl ether, dodecylvinyl ether, 2-chloroethylvinyl ether, ethylvinyl ether; unsaturated acids such as acrylic acid, methacrylic acid, alpha-chloro acrylic acid,


10 crotonic acid, maleic acid, fumaric acid, itaconic acid and their anhydrides and their esters such as vinyl, allyl, methyl, butyl, isobutyl, hexyl, heptyl, 2-ethylhexyl, cyclohexyl, lauryl, stearyl, isobornyl or alkoxy ethyl acrylates and methacrylates; alpha-beta unsaturated nitriles such as acrylonitrile, methacrylonitrile, 2-chloroacrylonitrile, 2-cyanoethyl acrylate, alkyl cyanoacrylates; alpha,beta-

15 unsaturated carboxylic acid derivatives such as allyl alcohol, allyl glycolate, acrylamide, methacrylamide, n-diisopropyl acrylamide, diacetoneacrylamide, N,N-diethylaminoethylmethacrylate, N-t-butylamino ethyl methacrylate; styrene and its derivatives such as vinyltoluene, alpha-methylstyrene, alpha-cyanomethyl styrene; lower olefinic hydrocarbons which can contain halogen such as ethylene, propylene,

20 isobutene, 3-chloro-1-isobutene, butadiene, isoprene, chloro and dichlorobutadiene and 2,5-dimethyl-1,5-hexadiene, and allyl or vinyl halides such as vinyl and vinylidene chloride. Preferred non-fluorinated monomers include hydrocarbon group containing monomers such as those selected from octadecylmethacrylate, laurylmethacrylate, butylacrylate, N-methylol acrylamide, isobutylmethacrylate,

25 ethylhexyl acrylate and ethylhexyl methacrylate; and vinylchloride and vinylidene chloride.

The fluorochemical silane of the invention may further include units M^a which are derivable from a monomer represented by the formula :



(VI)

wherein each of Y^4 , Y^5 and Y^6 independently represents an alkyl group, an aryl group, a hydrolysable group including hydrolyzable water solubilizing group as well as other hydrolyzable groups that are not water solubilizing; Z represents an organic

5 divalent linking group and E^2 represents a free radical polymerizable group such as for example listed above with respect to E^1 . By the term "derivable from" is meant that the units M^a derive directly from the free radical polymerization of the monomers according to formula (VI) as well as indirectly by further reaction of the silyl groups included in the oligomer upon polymerization of monomers according

10 to formula (VI). In particular, as will be described in more detail below, a water solubilising group may be introduced into the fluorochemical silane after a polymerization or oligomerization involving a monomer according to formula (VI) by reacting the resulting silyl group with a compound that includes a water solubilising group and that can displace a substituent on the silicone atom.

15

The organic divalent linking group Z preferably contains from 1 to about 20 carbon atoms. Z can optionally contain oxygen, nitrogen, or sulfur-containing groups or a combination thereof, and Z is preferably free of functional groups that substantially interfere with free-radical oligomerization (e.g., polymerizable olefinic double

20 bonds, thiols, and other such functionality known to those skilled in the art).

Examples of suitable linking groups Z include straight chain, branched chain or cyclic alkylene, arylene, aralkylene, oxyalkylene, carbonyloxyalkylene, oxycarboxyalkylene, carboxyamidoalkylene, urethanealkylene, ureylenealkylene and combinations thereof. Preferred linking groups are selected from the group


25 consisting of alkylene, oxyalkylene and carbonyloxyalkylene.

Y^4 , Y^5 and Y^6 independently represents an alkyl group, an aryl group, a hydrolysable group or a hydrolyzable water solubilizing group. Typical examples of

hydrolyzable groups include halogen, alkoxy, acyloxy, acyl or aryloxy groups.

Hydrolysable water solubilizing groups are as disclosed above.

Monomers according to formula VI that include a hydrolysable water solubilising group can conveniently be prepared starting from monomers represented by formula VII



VII

wherein each of Y^7 , Y^8 and Y^9 independently represents an alkyl group, an aryl group or a hydrolyzable group, selected from halogen, alkoxy groups, acyloxy groups, acyl groups and aryloxy groups with the proviso that at least one of Y^7 , Y^8 and Y^9 represent a hydrolyzable group. Z and E^2 are as defined above. The monomers of formula VII can be reacted with poly(oxyalkylene) group containing compounds capable of displacing a hydrolyzable group in the monomer of formula VII. Examples of monomers according to formula VII include vinyltrichlorosilane, vinyltrimethoxysilane, vinyltriethoxysilane and alkoxysilane functionalised acrylates or methacrylates, such as methacryloyloxypropyl trimethoxysilane. The monomers of formula VI can conveniently be prepared by exchange reaction of the hydrolyzable group, preferably alkoxy or aryloxy, in compounds of formula VII with a hydrolyzable water solubilizing group, such as e.g. a poly(oxyalkylene) group. Typical examples of poly(oxyalkylene) group containing compounds include alkyl ethers of polyglycols such as e.g. methyl or ethyl ether of polyethyleneglycol, hydroxy terminated methyl or ethyl ether of a random or block copolymer of ethyleneoxide and propyleneoxide, amino terminated methyl or ethyl ether of polyethyleneoxide. Suitable examples include methoxydiethyleneglycol, methoxytriethyleneglycol, Carbowax™ 350, Carbowax™ 550 and Carbowax™ 750. The hydrolyzable group exchange reaction is conveniently carried out neat, in the presence of an inhibitor, such as methyl ethyl hydroquinone (MEHQ) or phenothiazine in order to prevent polymerization of the monomer. The reaction can

be done at a temperature between 60 °C and 200°C, preferably 80°C to 180°C, during 5 to 8 hours. Ionic hydrolyzable water solubilizing groups can be introduced by reacting the compounds of formula VII with an alcohol or amine that is functionalised with an ionic group. Examples thereof include

- 5 HOCH₂CH₂N⁺(CH₃)₃I⁻, HOCH₂CH₂N⁺(CH₃)₂CH₂CH₂CH₂SO₃⁻ and
HOCH₂CH₂N⁺(CH₃)₃Cl⁻.

The fluorochemical silane is conveniently prepared through a free radical polymerization of a fluorinated monomer with optionally a non-fluorinated monomer and a monomer containing a silyl group in the presence of a chain transfer agent. A free radical initiator is generally used to initiate the polymerization or oligomerization reaction. Commonly known free-radical initiators can be used and examples thereof include azo compounds, such as azobisisobutyronitrile (ABIN), azo-2-cyanovaleric acid and the like, hydroperoxides such as cumene, t-butyl and t-amyl hydroperoxide, dialkyl peroxides such as di-t-butyl and dicumylperoxide, peroxyesters such as t-butylperbenzoate and di-t-butylperoxy phthalate, diacylperoxides such as benzoyl peroxide and lauroyl peroxide.


The oligomerization reaction can be carried out in any solvent suitable for organic free-radical reactions. The reactants can be present in the solvent at any suitable concentration, e.g., from about 5 percent to about 90 percent by weight based on the total weight of the reaction mixture. Examples of suitable solvents include aliphatic and alicyclic hydrocarbons (e.g., hexane, heptane, cyclohexane), aromatic solvents (e.g., benzene, toluene, xylene), ethers (e.g., diethylether, glyme, diglyme, diisopropyl ether), esters (e.g., ethyl acetate, butyl acetate), alcohols (e.g., ethanol, isopropyl alcohol), ketones (e.g., acetone, methylethyl ketone, methyl isobutyl ketone), sulfoxides (e.g., dimethyl sulfoxide), amides (e.g., N,N-dimethylformamide, N,N-dimethylacetamide), halogenated solvents such as methylchloroform, FREON™113, trichloroethylene, α,α,α-trifluorotoluene, and the like, and mixtures thereof.

The oligomerization reaction can be carried out at any temperature suitable for conducting an organic free-radical reaction. Particular temperature and solvents for use can be easily selected by those skilled in the art based on considerations such as the solubility of reagents, the temperature required for the use of a particular
 5 initiator, molecular weight desired and the like. While it is not practical to enumerate a particular temperature suitable for all initiators and all solvents, generally suitable temperatures are between about 30° C. and about 200° C.

The fluorochemical oligomer is prepared in the presence of chain transfer agent.

10 Suitable chain transfer agents typically include a hydroxy-, amino-, or mercapto group. The chain transfer agent may include two or more of such hydroxy, amino- or mercapto groups. Typical chain transfer agents useful in the preparation of the fluorochemical oligomer include those selected from 2-mercaptoethanol, 3-mercapto-2-butanol, 3-mercapto-2-propanol, 3-mercapto-1-propanol, 3-mercapto-
 15 1,2-propanediol, 2-mercapto-ethylamine, di(2-mercaptoethyl)sulfide, octylmercaptane and dodecylmercaptane.

In a preferred embodiment a chain transfer agent containing a silyl group having one or more hydrolyzable groups is used in the oligomerization to produce the
 20 fluorochemical oligomer. Transfer agents including a silyl group include those according to formula VIII.



VIII

wherein Y¹, Y² and Y³ each independently represents an alkyl group, preferably a C₁-C₈ alkyl group such as methyl, ethyl or propyl or an alkyl group containing a
 25 cycloalkyl such as cyclohexyl or cyclopentyl, an aryl group such as phenyl, an alkylaryl group or an aralkyl group, a hydrolysable group such as for example halogen, alkoxy groups such as methoxy or ethoxy, acyloxy groups, acyl groups or aryloxy groups or a hydrolysable water solubilizing group, such as a poly(oxyalkylene) group, with at least one of Y¹, Y² and Y³ representing a

hydrolysable group. L represents a divalent linking group such as -O-, -S- and -NR wherein R represents an alkyl or aryl group.

Preferred chain transfer agents are those in which L represents -S-Q¹- with Q¹ being linked to the silicone atom in formula VIII and wherein Q¹ represents an organic
5 divalent linking group such as for example a straight chain, branched chain or cyclic alkylene, arylene or aralkylene.

A single chain transfer agent or a mixture of different chain transfer agents may be used. The preferred chain transfer agents are 2-mercaptoethanol, octylmercaptane
10 and 3-mercaptopropyltrimethoxysilane. A chain transfer agent is typically present in an amount sufficient to control the number of polymerized monomer units in the oligomer and to obtain the desired molecular weight of the oligomeric fluorochemical silane. The chain transfer agent is generally used in an amount of about 0.05 to about 0.5 equivalents, preferably about 0.25 equivalents, per
15 equivalent of monomer including fluorinated and non-fluorinated monomers.

The fluorochemical silane of the present invention contains one or more hydrolyzable water solubilising groups. These hydrolysable water solubilising groups may be introduced in the fluorochemical silane by oligomerising in the
20 presence of a chain transfer agent having a silyl group containing one or more hydrolysable water solubilising groups, for example a chain transfer agent according to formula VIII above wherein at least one of Y¹, Y² and Y³ represents a hydrolysable water solubilising group and/or by co-oligomerising with a monomer containing a silyl group having one or more hydrolysable water solubilising groups.
25 such as a monomer according to formula VII above wherein at least one of Y⁷, Y⁸ and Y⁹ represents a hydrolysable water solubilising group. According to a more preferred embodiment, a silyl group containing one or more hydrolysable water solubilising groups is formed subsequent to the oligomerization or polymerization.

30 According to a first embodiment for introducing a silyl group containing one or more hydrolysable water solubilising groups subsequent to the oligomerization, a fluorochemical silane is first prepared by oligomerizing fluorinated monomer and

optional non-fluorinated monomer with one or more monomers according to formula VII above wherein at least one of Y^7 , Y^8 and Y^9 represents a hydrolysable group selected from an alkoxy group, an acyloxy group, an acyl group, an aryloxy group and a halogen such as chlorine in the presence of a chain transfer agent which may optionally also contain a silyl group such as for example a chain transfer agent according to formula VIII above wherein at least one of Y^1 , Y^2 and Y^3 represents a hydrolysable group selected from an alkoxy group, an acyloxy group, an acyl group, an aryloxy group and a halogen such as chlorine. Subsequent to the oligomerization, at least part of the hydrolysable groups are exchanged by hydrolysable water solubilising groups by reacting the fluorochemical silane with a compound containing the water solubilising groups and capable of displacing the hydrolysable groups of the silyl moieties in the fluorochemical silane. Examples of such compounds include in particular hydroxy or amino terminated polyoxyalkylene compounds such as for example alkyl ethers of polyglycols such as e.g. methyl or ethyl ether of polyethyleneglycol, hydroxy terminated methyl or ethyl ether of a random or block copolymer of ethyleneoxide and propyleneoxide, amino terminated methyl or ethyl ether of polyethyleneoxide. Specific examples include methoxydiethyleneglycol, methoxytriethyleneglycol, Carbowax™ 350, Carbowax™ 550 and Carbowax™ 750. Alcohols or amines functionalised with an ionic group as mentioned above can be used to introduce ionic hydrolysable water solubilising groups.


The exchange reaction is conveniently carried out immediately after the oligomerisation reaction, at a temperature between 60 °C and 200°C, preferably 80°C to 180°C, during 5 to 8 hours, while stripping off solvent and products formed as a result of the exchange reaction such as alcohol. Optionally a catalyst, such as paratoluene sulphonic acid, can be used. It is to be appreciated that the exchange reaction may be incomplete and reaction product may comprise mixtures of compounds.

As a variation to the above method for introducing the hydrolysable water solubilising groups, the oligomerization may be carried out without the use of the

silyl group containing monomer but with a chain transfer agent containing a silyl group. Upon the oligomerization, the hydrolyzable water solubilising groups may then again be introduced through the exchange reaction described above.

- 5 A further embodiment for producing the fluorochemical silane, involves the polymerisation or oligomerisation of one or more fluorinated monomers and a monomer having a functional group available for subsequent reaction such as for example a hydroxy group or amino group in the presence of a chain transfer agent. Examples of such monomers include hydroxy or amino functionalised acrylate or methacrylates, such as 2-hydroxyethyl(meth)acrylate, 3-hydroxypropyl(meth)acrylate, 6-hydroxyhexyl(meth)acrylate and the like. Alternative to or in addition to the use of functionalised monomer, a functionalised chain transfer agent can be used. For example, a chain transfer agent can be used that is functionalised with a group such as a hydroxy group or an amino group.
- 15 Examples of such chain transfer agents include 2-mercaptoethanol, 3-mercapto-2-butanol, 3-mercapto-2-propanol, 3-mercapto-1-propanol, 3-mercapto-1,2-propanediol and 2-mercapto-ethylamine. Subsequent to the oligomerisation the functional group contained in the comonomer and/or chain transfer agent can be reacted with a compound including a silyl group having hydrolysable groups and that is capable of reacting with the functional group contained in the comonomer and/or chain transfer agent.
- 20

Suitable compounds for reacting with the functional groups included in the monomer or chain transfer agent include compounds according to the following formula :



IX

wherein A represents a functional group capable of undergoing a condensation reaction with the functional group contained in the monomer or chain transfer agent, in particular a functional group capable of condensing with a hydroxy or amino

functional oligomer. Examples of A include an isocyanate or an epoxy group. Q⁵ represents an organic divalent linking group, Y^a, Y^b and Y^c each independently represents an alkyl group, preferably a C₁-C₈ alkyl group such as methyl, ethyl or propyl or an alkyl group containing a cycloalkyl such as cyclohexyl or cyclopentyl, an aryl group such as phenyl, an alkylaryl group or an aralkyl group or hydrolysable group such as for example halogen, an alkoxy group such as methoxy or ethoxy, an acyloxy group, an acyl group or an aryloxy group and at least one of Y^a, Y^b and Y^c represents a hydrolysable group. Examples of organic divalent linking groups Q⁵ include straight chain, branched chain or cyclic alkylene, arylene, aralkylene, oxyalkylene, carbonyloxyalkylene, oxycarboxyalkylene, carboxyamidoalkylene, urethanealkylene, ureylenealkylene and combinations thereof. Preferred linking groups are selected from the group consisting of alkylene, oxyalkylene and carbonyloxyalkylene.


- 15 Examples of compounds according to formula IX include 3-isocyanatopropyltrimethoxysilane and 3-epoxypropyltrimethoxysilane.

The condensation reaction is carried out under conventional conditions well-known to those skilled in the art. Preferably the reaction is run in the presence of a catalyst. Suitable catalysts include tin salts such as dibutyltin dilaurate, stannous octanoate, stannous oleate, tin dibutyldi-(2-ethyl hexanoate), stannous chloride; and others known to those skilled in the art. The amount of catalyst present will depend on the particular reaction, and thus it is not practical to recite particular preferred concentrations. Generally, however, suitable catalyst concentrations are from about 0.001 percent to about 10 percent, preferably about 0.1 percent to about 5 percent, by weight based on the total weight of the reactants.

The condensation reaction is preferably carried out under dry conditions in a polar solvent such as ethyl acetate, acetone, methyl isobutyl ketone, toluene and the like. Suitable reaction temperatures will be easily determined by those skilled in the art based on the particular reagents, solvents, and catalysts being used. Suitable temperatures are between about room temperature and about 120 deg. C.

Subsequent to the condensation reaction with a compound according to formula IX, one or more of the hydrolysable groups in the silyl groups on the oligomer are exchanged with a hydrolysable water solubilising group in an exchange reaction as described above.


In case a functionalised chain transfer agent as set forth above is used in the oligomerization, the condensation reaction of the oligomer with a compound according to formula IX wherein A is an isocyanate group and the further exchange reaction generally results in fluorochemical silane oligomers that have an organic residue G (formula I) which can be represented by formula X:




X

wherein Q¹ and Q⁵ each independently represents an organic divalent linking group, T² represents O or NR with R being a hydrogen or an aryl or a C₁-C₄ alkyl group, Y¹, Y² and Y³ are as defined above and at least one of Y¹, Y² and Y³ represents a hydrolysable water solubilising group.

When a compound according to formula IX wherein A is an epoxy group is used, the organic residue may be represented by a residue according to formula XI or XII or a mixture thereof:



XI



XII

wherein Q^1 , Q^5 , T^2 and Y^1 , Y^2 and Y^3 have the meaning as defined above in formula X.

- 5 After preparation of the fluorochemical silane according to any of the methods described above, the fluorochemical silane may be isolated by evaporating any solvents used in the preparation. A solution or dispersion in water can be made by vigorously stirring the fluorochemical silane in water at neutral pH, typically at a temperature between 20 and 70°C, preferably between 30 and 50°C and during a
- 10 time sufficient to dissolve or disperse the product. The aqueous solutions or dispersions prepared typically have a stability of at least 1 hour, preferably at least 4 hours, more preferably at least 24 hours. Additional emulsifiers can be used to increase the dispersion stability, but are generally avoided in order not to obtain a substrate with optimal repellency properties, in particular water repellency. Other
- 15 components, such as silica or TiO_2 , can be present, as well as other aqueous water extenders known to those skilled in the art. Examples include silicones, siloxanes, melamines, urethanes and the like.

The hydrolysable fluorochemical silane can be used to treat substrates so as to

20 render these oil and water repellent and/or to provide stain repellency to such substrates. Suitable substrates that can be treated in a particularly effective way with the water soluble or dispersible fluorochemical silanes of this invention include substrates having a hard surface that preferably has groups capable of reacting with the fluorochemical silane according to formula (I). Preferably, such reactivity of

25 the surface of the substrate is provided by active hydrogen atoms. When such active hydrogen atoms are not present, the substrate may first be treated in a plasma containing oxygen or in a corona atmosphere to make them reactive to the fluorochemical silane. Particularly preferred substrates include ceramics, glass, metal, natural and man-made stone, thermoplastic materials (such as

poly(meth)acrylate, polycarbonate, polystyrene, styrene copolymers, such as styrene acrylonitrile copolymers, polyesters, polyethylene terephthalate), paints (such as those on acrylic resins), powder coatings (such as polyurethane or hybrid powder coatings), and wood. Various articles can be effectively treated with the

5 fluorochemical silane solution of the present invention to provide a water and oil repellent coating thereon. Examples include ceramic tiles, bathtubs or toilet pots, glass shower panels, construction glass, various parts of a vehicle (such as the mirror or windscreen), glass, ceramic or enamel pottery materials.

10 Treatment of the substrates results in rendering the treated surfaces less retentive of soil and more readily cleanable due to the oil and water repellent nature of the treated surfaces. These desirable properties are maintained despite extended exposure or use and repeated cleanings because of the high degree of durability of the treated surface as can be obtained through the compositions of this invention.

15 To effect the treatment of a substrate, the fluorochemical silane, preferably in the form of an aqueous composition as disclosed above, is applied to the substrate. The amount of hydrolysable fluorochemical silane to be coated on the substrate will generally be that amount sufficient to produce a coating which is water and oil

20 repellent, such a coating having at 20°C a contact angle with distilled water of at least 80°, and a contact angle with n-hexadecane of at least 40°, measured after drying and curing of the coating. This coating can be extremely thin, e.g. 1 to 50 molecular layers, though in practice a useful coating may be thicker.

25 Preferably, the substrate should be clean prior to applying the compositions of the invention so as to obtain optimum characteristics, particularly durability. That is, the surface of the substrate to be coated should be substantially free of organic contamination prior to coating. Cleaning techniques depend on the type of substrate and include, for example, a solvent washing step with an organic solvent, such as
30 acetone or ethanol. The coating composition is typically a relatively diluted aqueous composition, containing between 0.01 and 10 percent by weight of the fluorochemical silane, more preferably, between 0.03 and 3 percent by weight of

the fluorochemical silane, and most preferably, between 0.1 and 2 percent by weight of the fluorochemical silane.

For ease of manufacturing and for reasons of costs, the compositions of the present invention will generally be prepared shortly before use by dispersing the fluorochemical silane of formula (I) in water. The composition should generally be free of acidic and basic substances to avoid premature hydrolysis of the hydrolysable water solubilising groups which could cause coagulation or settling out of the fluorochemical silane. A thus freshly prepared diluted solution will generally be stable for 1 or more days.

A wide variety of coating methods can be used to apply a composition of the present invention, such as brushing, spraying, dipping, rolling, spreading, and the like. A preferred coating method for application of a fluorochemical silane of the present invention includes spray application. Generally, the fluorochemical silane coating on the substrate will be subjected to heat. To effect heating, a substrate to be coated can typically be preheated at a temperature of for example between 60°C and 150°C. This is of particular interest for industrial production, where eg. ceramic tiles can be treated immediately after the baking oven at the end of the production line. Alternatively, the substrate to be coated can be contacted with the treating composition at room temperature (typically, about 20°C to about 25°C) and subsequently dried at elevated temperature of e.g. 40° to 300°C. Following application, the treated substrate is typically polished with an acid or base solution to remove the hydrolyzable water solubilizing groups.

Although the inventors do not wish to be bound by theory, compounds of the above formula I are believed to undergo reaction with the substrate surface to form a siloxane layer. For the preparation of a durable hydrophobic coating, an acid or a base catalyst should be present in order to cause hydrolysis of the water solubilizing silane end groups, and then condensation of the resulting silanol groups on and to the substrate. In this context, "siloxane" refers to -Si-O-Si- bonds to which are attached fluorochemical oligomer segments as given in formula I. A coating prepared from a

coating composition that includes compounds of formula I can also include unreacted or uncondensed silanol groups.

- To achieve good hydrophobicity and durability, organic or inorganic acid or base catalyst should be used. Organic acids include acetic acid, citric acid, formic acid, triflic acid, perfluorobutyric acid and the like. Examples of inorganic acids include sulphuric acid, hydrochloric acid and the like. Examples of useful amines include sodium hydroxide, potassium hydroxide and triethylamine. The acid or base catalyst will generally be applied to the coating after drying as a water based solution comprising between about 0.01 and 10%, more preferably between 0.05 and 5% by weight of the catalyst.

EXAMPLES

- The following examples further illustrate the invention without the intention however to limit the invention thereto. All parts are by weight unless indicated otherwise.

Abbreviations

- 20 Aca : acetic acid, available from Aldrich
CW 550 : Carbowax™ 550, methoxy polyethyleneglycol with average molecular weight 550, available from Aldrich
CW 350 : Carbowax™ 350, methoxy polyethyleneglycol with average molecular weight 350, available from Aldrich
25 MeFOSEA : N-methyl perfluorooctyl sulfonamido ethylacrylate
MeFBSEA : N-methyl perfluorobutyl sulfonamido ethylacrylate
A-174 : $\text{CH}_2 = \text{C}(\text{CH}_3)\text{C}(\text{O})\text{O}(\text{CH}_2)_3 \text{Si}(\text{OCH}_3)_3$, available from Aldrich
A-160 : $\text{HS}(\text{CH}_2)_3\text{Si}(\text{OCH}_3)_3$, available from Aldrich
TEG : $\text{HOCH}_2\text{CH}_2\text{OCH}_2\text{CH}_2\text{OCH}_2\text{CH}_2\text{OCH}_3$, available from Aldrich
30 Dynasylan™ 8800 : waterbased fluorochemical, available from Degussa-Hüls
FC-759 : waterbased fluorochemical, available from 3M
FC-405 : solvent based fluorochemical, available from 3M

Methods of application and testing

Coating method

In a first step, the substrates were cleaned and degreased with acetone. After
5 cleaning, the substrates were preheated to 150°C. 1 % aqueous mixtures of
fluorochemical silanes as given in the respective examples were applied onto the hot
substrates, by spray application at about 20 ml/minute.

After drying, the substrates were treated with a 3 % solution of acetic acid in water.
During this cleaning step, the initial hydrophilic coating transformed into a
10 hydrophobic coating. The substrates were dried and cured at 150°C during 15
minutes.

Contact angles

The treated substrates were tested for their contact angles versus water (W) and
15 n-hexadecane (O) using an Olympus TGHM goniometer. The contact angles were
measured before (initial) and directly after abrasion (abrasion), unless otherwise
indicated. The values are the mean values of 4 measurements and are reported in
degrees. The minimum measurable value for a contact angle was 20. A value < 20
meant that the liquid spread on the surface.

Abrasion test

The treated substrates were abraded using an Erichsen cleaning machine, 3M High
Performance Cloth (available from 3M) and CIF cleaner (available from Lever),
using 40 cycles.

Synthesis of fluorochemical silanes (FCSIL)

Several fluorochemical silanes as given in table 1 were prepared similar to the 2 step
synthesis of MeFOSEA/A-174/A-160/CW550 (molar ratio : 2/2/1/13.5) (FCSIL1)

:

30 In a first step, a fluorochemical oligomer MeFOSEA/A-174/A-160 2/2/1 was
prepared.

In a three-necked flask of 500 ml, fitted with a condenser, stirrer and thermometer, were placed 36.7 g (0.06 mol) MeFOSEA, 14.9 g (0.06 mol) A-174, 7.8 g (0.03 mol) A-160, 130 g ethylacetate and 0.1 g ABIN.

The mixture was degassed three times using aspirator vacuum and nitrogen

- 5 pressure. The mixture was reacted under nitrogen at 75°C during 8 hours. An additional 0.05 g ABIN was added and the reaction was continued for another 16 hrs at 75°C; another 0.05 g ABIN was added and reaction continued at 82°C for 2 hrs. A clear solution of the oligomeric fluorochemical silane MeFOSEA/A-174/A-160 in a molar ratio 2/2/1 was obtained.
- 10 In a second step, 220 g (0.4 moles) Carbowax™ 550 and 20 g heptane were added. The alkoxide exchange reaction was done at a temperature of 100-180°C for 6 hrs, while stripping off solvent and exchanged ethanol. A brown, clear solution was obtained which upon cooling became solid. A 1% dispersion in water was made by vigorous stirring for 15 minutes at 40°C.
- 15 Further examples were prepared using above procedure, using molar ratios of reactants as indicated in table 1. Comparative fluorochemical silanes C-FCSIL 1-3 were prepared according to US5,274,159, example 2.

Table 1 : Composition of fluorochemical silanes

FCSIL	Composition	Molar ratio
1	MeFOSEA/A-174/A-160/CW550	2/2/1/13.5
2	MeFOSEA/A-174/A-160/CW550	1/4/1/22.5
3	MeFOSEA/A-174/A-160/TEG	1/4/1/22.5
4	MeFOSEA/A-174/A-160/CW550	4/4/1/22.5
5	MeFOSEA/A-174/octylmercaptane/TEG	1/4/1/18
6	MeFBSEA/A-160/CW350	4/1/4.5
7	MeFBSEA/A-174/A-160/TEG	1/4/1/22.5
8	MeFBSEA/A-174/A-160/TEG	2/2/1/13.5
9	MeFBSEA/A-174/A-160/TEG	4/4/1/22.5
10	MeFBSEA/A-174/A-160/TEG	6/3/1/18
11	MeFBSEA/A-174/A-160/TEG	10/10/1/50

12	MeFBSEA/A-174/mercaptoethanol/TEG	2/2/1/9
13	MeFBSEA/A-174/mercaptoethanol/ isocyanatopropyltrimethoxysilane/TEG	2/2/1/1/13.5
C-FCSIL-1	$C_8F_{17}SO_2N(Et)(CH_2)_3Si(TEG)_3$	
C-FCSIL-2	$C_8F_{17}SO_2N(Et)(CH_2)_3Si(CW550)_3$	
C-FCSIL-3	$C_4F_9SO_2N(Me)(CH_2)_3Si(TEG)_3$	

Examples 1 to 5 and comparative examples C-1 to C-5

In examples 1 to 5, white glazed Katayha tiles (7.5 cm x 7.5 cm), were coated with 1% aqueous fluorochemical silane solutions as given in table 2, according to the general method. Comparative examples C-1 and C-2 were made in the same way with comparative treating agents as given in table 2. Comparative example C-3 was made with a solvent based (ethanol) fluorochemical treating agent FC-405. Comparative examples C-4 and C-5 were made with commercially available water based fluorochemical treating agents for ceramic and porous stone surfaces. Contact angles were measured before and after abrasion with an Erichsen cleaning machine. The results are given in table 2.

Table 2 : Contact angles of wall tiles treated with fluorochemical silanes

Ex	Treating agent	Contact angles (°)			
		Initial W	Initial O	After abrasion W	After abrasion O
1	FCSIL-1	110	68	80	52
2	FCSIL-2	105	66	75	50
3	FCSIL-3	111	69	85	50
4	FCSIL-4	108	65	72	49
5	FCSIL-5	114	67	76	51
C-1	C-FCSIL-1	100	62	66	38
C-2	C-FCSIL-2	80	47	60	40
C-3	FC-405 (applied at 2%, from ethanol)	105	62	76	45
C-4	FC-759 (applied at 6%)	75	55	45	35

C-5	Dynasylan™ 8800 (applied at 6%)	90	55	54	30
-----	---------------------------------	----	----	----	----

The results indicated that tiles with high oil and water repellency could be made by using fluorochemical silanes according to the invention. High contact angles were measured, initially, but especially also after abrasion, indicating that highly durable coatings were made. The performance of the treated tiles was superior compared to tiles treated with commercially available treating agents. As can be seen from the results of examples 1 to 5 compared to C-1 and C-2, there was an advantage, especially in oil repellency, in using fluorochemical silane oligomers, compared to the fluorochemical compound. Account needs to be taken that a difference in contact angle with distilled water of 10° and a difference in contact angle with n-hexadecane of 5° is considered to be significant.

Examples 6 to 13 and comparative example C-6

In examples 6 to 13 and comparative example C-6, the same kind of experiment was repeated with fluorochemical silane compounds as given in table 3. The compositions of the treating agents and the contact angles of Katayha tiles treated therewith are given in table 3.

Table 3 : Katayha tiles treated with fluorochemical silane compounds

Ex	Treating agent	Contact angles (°)			
		Initial W	Initial O	After abrasion W	After abrasion O
6	FCSIL-6	97	64	60	32
7	FCSIL-7	93	61	59	35
8	FCSIL-8	97	57	55	29
9	FCSIL-9	95	60	65	32
10	FCSIL-10	102	60	58	35
11	FCSIL-11	95	58	55	29
12	FCSIL-12	85	55	60	33
13	FCSIL-13	90	57	58	37

C-6	C-FCSIL-3 (applied at 5%)	78	45	45	25
-----	---------------------------	----	----	----	----

Also in these experiments, tiles with high oil and especially water repellency were obtained by using fluorochemical silanes according to the invention. High contact angles were measured, initially and also after abrasion, indicating that highly durable
5 coatings were made. The fluorochemical oligomer silanes (applied at 1%) clearly showed higher performance than the fluorochemical silane compound (applied at 5%).


THIS PAGE BLANK (USPTO)

25 01. 2001

CLAIMS

63

1. A water soluble or water dispersible fluorochemical silane represented by the general formula:




(I)

wherein X represents the residue of an initiator or hydrogen;

M^f represents units derived from one or more fluorinated monomers;

M^h represents units derived from one or more non-fluorinated monomers;

M^a represents units having a silyl group represented by the formula:



(II)

wherein each of Y^4 , Y^5 and Y^6 independently represents an alkyl group, an aryl group or a hydrolyzable group;

G is a monovalent organic group comprising the residue of a chain transfer agent;

n represents a value of 1 to 100;


m represents a value of 0 to 100;

and r represents a value of 0 to 100;

and $n+m+r$ is at least 2;

with the proviso that at least one of the following conditions is fulfilled: (a) G

contains a silyl group of the formula:



(III)

wherein Y^1 , Y^2 and Y^3 each independently represents an alkyl group, an aryl group or a hydrolyzable group and at least one of Y^1 , Y^2 and Y^3 represents a hydrolyzable water solubilising group or

(b) r is at least 1 and at least one of Y^4 , Y^5 and Y^6 represents a hydrolyzable water solubilizing group.

2. A water soluble or water dispersible fluorochemical silane according to claim 1
5 wherein said hydrolyzable water solubilizing group is an ionic group or a non-ionic group comprising a polyoxyalkylene group having 2 or 3 carbon atoms.


3. A water soluble or water dispersible fluorochemical silane according to claim 1
10 wherein r is 0 and wherein at least one of Y^1 , Y^2 and Y^3 represents a polyoxyalkylene group having 2 or 3 carbon atoms.

4. A water soluble or water dispersible fluorochemical silane according to claim 1
15 wherein r is an integer of 1 to 30 and wherein at least one of Y^4 , Y^5 and Y^6 represents a polyoxyalkylene group having 2 or 3 carbon atoms.

5. A water soluble or water dispersible fluorochemical silane wherein $m < n$.

6. A water soluble or water dispersible fluorochemical silane according to any of
20 the previous claims wherein the fluorochemical silane according to formula (I) contains at least 20 % by weight of water solubilizing groups.


7. A water soluble or water dispersible fluorochemical silane according to any of
the previous claims wherein said unit M^f is derived from an ethylenically unsaturated monomer corresponding to the formula:



25 wherein R_f represents a fluoroaliphatic group comprising at least 3 carbon atoms or a fluorinated polyether group, Q represents an organic divalent linking group and E^1 represents a free radical polymerizable group.

30 8. A water soluble or water dispersible fluorochemical silane according to claim 7 wherein R_f represents C_4F_9- .

9. A water soluble or water dispersible fluorochemical silane according to any of the previous claims wherein said unit M^a is derivable from a monomer represented by the formula:



5

wherein Y^4 , Y^5 and Y^6 have a meaning as defined in claim 1, Z represents an organic divalent linking group and E^2 represents a free radical polymerizable group.

10. A water soluble or water dispersible fluorochemical silane according to any of the previous claims wherein said water soluble or water dispersible fluorochemical silane has a water solubility or water dispersibility of at least 0.1 % by weight.
11. An aqueous composition comprising a water soluble or water dispersible fluorochemical silane as defined in any of claims 1 to 10.
12. Method of treatment of a substrate comprising applying a water soluble or water dispersible fluorochemical silane as defined in any of claims 1 to 10 or an aqueous composition as defined in claim 11 on a substrate.
13. Method according to claim 12 further comprising the step of heating to a temperature of 40°C to 300°C.
14. Method according to claim 12 or 13 wherein said fluorochemical silane or an aqueous composition thereof is applied to said substrate in the presence of an acid or base catalyst or wherein subsequent to application of said fluorochemical silane or an aqueous composition thereof, an acid or base catalyst is applied.


15. Method according to any of claims 13 to 14 wherein said substrate is selected from the group consisting of ceramics, glass, stone, plastic and metal.

16. Treated substrate obtainable by any of the methods of claims 12 to 15.

5

17. Method of making a water soluble or water dispersible fluorochemical silane as defined in any of claims 1 to 10 comprising a free radical polymerization of fluorinated monomer and optionally a non-fluorinated monomer in the presence of a chain transfer agent wherein at least said chain transfer agent contains a silyl group represented by the formula:


10



wherein Y^1 , Y^2 and Y^3 each independently represents an alkyl group, an aryl group or a hydrolyzable group and at least one of Y^1 , Y^2 and Y^3 represents a hydrolyzable water solubilising group;

15

and/or wherein said free radical polymerization involves copolymerization with a monomer having a silyl group represented by formula:




wherein each of Y^4 , Y^5 and Y^6 independently represents an alkyl group, an aryl group or a hydrolyzable group and at least one of Y^4 , Y^5 and Y^6 represents a hydrolyzable water solubilising group.

20

18. A method for making a water soluble or water dispersible fluorochemical silane as defined in any of claims 1 to 10 comprising preparation of a fluorochemical oligomer by free radical polymerization of a fluorinated monomer, optionally a

non-fluorinated monomer in the presence of a chain transfer agent and at least said chain transfer agent contains a silyl group represented by the formula:




(A)

wherein Y^a , Y^b and Y^c each independently represents an alkyl group, an aryl group and at least one of Y^a , Y^b and Y^c represents a hydrolyzable group selected from an alkoxy group, an acyloxy group, an acyl group, an aryloxy group and a halogen;

and/or wherein said free radical polymerization involves copolymerization with a monomer having a silyl group represented by the above formula (A);

and wherein the thus obtained fluorochemical oligomer is further reacted with a compound containing water solubilising groups and which compound is capable of displacing one or more of the hydrolysable groups in the silyl moiety according to formula (A) above so as to introduce into said silyl moiety one or more hydrolysable water solubilising groups.

19. A method for making a water soluble or water dispersible fluorochemical silane as defined in any of claims 1 to 10 comprising (a) preparation of a fluorochemical oligomer by free radical polymerization of a fluorinated monomer and optionally a non-fluorinated monomer in the presence of a chain transfer agent and said chain transfer agent and/or a comonomer having a functional group available for further reaction after said free radical polymerization and being selected from the group consisting of a hydroxy group and an amino group (b) reacting a thus prepared fluorochemical oligomer with a compound according to the formula



(B)

wherein A represents a functional group capable of undergoing a condensation reaction with said functional group of said comonomer or said functional group of said chain transfer agent, Q^5 represents an organic divalent linking group, Y^a , Y^b and Y^c each independently represents an alkyl group or an aryl group and at least one of Y^a , Y^b and Y^c represents a hydrolysable group selected from the group consisting of halogen, an alkoxy group, an acyloxy group, an acyl group and an aryloxy group; and

(c) further reacting the thus obtained product with a compound containing water solubilising groups and which compound is capable of displacing one or more of the hydrolysable groups in the silyl moiety according to formula (B) above so as to introduce into said silyl moiety one or more hydrolysable water solubilising groups.

20. Method according to claim 18 or 19 wherein said compound containing water solubilising groups is a polyalkyleneoxide compound having a hydroxy or amino group.

21. A method according to claim 20 wherein said polyalkyleneoxide compound is a hydroxy or amino terminated C_1 - C_4 alkyl ether of a polymer of ethylene oxide and/or propylene oxide.

22. A method according to claim 20 wherein said polyalkyleneoxide compound is a C_1 - C_4 alkoxy polyalkyleneglycol wherein the alkylene of the polyalkylene glycol has 2 or 3 carbon atoms.

25 01. 2001


ABSTRACT

63

WATER SOLUBLE OR WATER DISPERSIBLE FLUOROCHEMICAL SILANES FOR RENDERING SUBSTRATES OIL AND WATER RELLENT

5

The present invention provides a water soluble or water dispersible fluorochemical silane represented by the general formula:




(I)

wherein X represents the residue of an initiator or hydrogen;

10 M^f represents units derived from one or more fluorinated monomer;

M^h represents units derived from one or more non-fluorinated monomer;

M^a represents units having a silyl group represented by the formula:



(II)

wherein each of Y^4 , Y^5 and Y^6 independently represents an alkyl group, an
15 aryl group or a hydrolyzable group;

G is a monovalent organic group comprising the residue of a chain transfer agent;


n represents a value of 1 to 100;

m represents a value of 0 to 100;

and r represents a value of 0 to 100;

20 and $n+m+r$ is at least 2;

with the proviso that at least one of the following conditions is fulfilled: (a) G contains a silyl group of the formula:



(III)

wherein Y^1 , Y^2 and Y^3 each independently represents an alkyl group, an aryl group or a hydrolyzable group and at least one of Y^1 , Y^2 and Y^3 represents a hydrolyzable water solubilising group or

- (b) r is at least 1 and at least one of Y^4 , Y^5 and Y^6 represents a hydrolyzable water
5 solubilizing group.